



Polyvinyl Alcohol in Eco-Friendly Films: Overcoming Challenges for a Sustainable Future

Rajshree P. Gadpayale

Assistant Professor

Department of Physics

Arts commerce and Science College, Maregaon, Dist. Yavatmal

Corresponding Author – Rajshree P. Gadpayale

DOI - 10.5281/zenodo.15259264

Abstract:

Polyvinyl alcohol (PVA) has emerged as a promising material for biodegradable films due to its water solubility, biocompatibility, and excellent film-forming properties. As global concerns over plastic pollution intensify, PVA-based biodegradable films are gaining attention for applications in food packaging, agriculture, and biomedical industries. This Paper explores the key properties of PVA that make it suitable for biodegradable film applications, including its mechanical strength, barrier properties, and environmental degradability. Various strategies to enhance PVA's performance, such as blending with natural polymers (e.g., starch, chitosan, cellulose) and incorporating nanomaterial are examined. However, challenges remain, including PVA's sensitivity to moisture, limited degradation under certain environmental conditions, and cost-related concerns for large-scale production. Solutions such as crosslinking, surface modifications, and the use of eco-friendly additives are discussed to improve the functional properties of PVA-based films. Additionally, this paper highlights recent advancements in sustainable PVA film production and biodegradability assessments. Future research directions focus on enhancing biodegradability, reducing environmental impact, and expanding applications in sustainable packaging solutions. By addressing these challenges, PVA-based biodegradable films hold significant potential as an eco-friendly alternative to conventional plastics.

Keywords: Biodegradable, Polymers, Biocompatibility, Sustainable

Introduction:

Polyvinyl Alcohol (PVA) has emerged as a promising polymer due to its excellent water solubility, biocompatibility, and biodegradability. PVA is a synthetic polymer that is both versatile and environmentally friendly, making it suitable for a wide range of applications, including biodegradable films for food packaging, agriculture, and medical uses [1][2]. The ability of PVA to form films that dissolve or degrade in water makes it a strong candidate for use in applications where rapid biodegradation is desirable. Unlike conventional plastics, PVA-based films can

degrade in natural environments, particularly in aquatic systems, without leaving behind harmful microplastics. As such, PVA has garnered considerable attention as a biodegradable packaging material that could help mitigate plastic waste, especially in food packaging and agricultural films, where single-use plastics are prevalent. However, despite its advantages, the widespread adoption of PVA-based biodegradable films is limited by certain challenges. For example, PVA is highly sensitive to moisture, which can compromise the mechanical properties and integrity of the

films under humid or wet conditions. Furthermore, while PVA is biodegradable, its degradation rate depends on environmental factors such as temperature, humidity, and the presence of microorganisms [3]. Additionally, PVA films often suffer from relatively poor mechanical strength and flexibility when compared to conventional plastics, which limits their practical applications, particularly in packaging materials that must withstand handling and transportation stresses.

This paper explores the role of PVA in the development of biodegradable films, focusing on the challenges and opportunities in optimizing its performance. The review will examine the key factors that affect the production and use of PVA-based biodegradable films, including material modifications, environmental factors, and sustainability considerations. Finally, it will discuss emerging trends and future research directions aimed at improving the practicality and scalability of PVA-based biodegradable films in commercial applications.

Properties of Polyvinyl Alcohol for Biodegradable Films:

The chemical and physical properties of Polyvinyl Alcohol (PVA) are largely influenced by the degree of hydrolysis, which refers to how much of the ester groups in polyvinyl acetate (PVA's precursor) are converted into hydroxyl groups. This hydrolysis process determines the PVA grade, which in turn affects its molecular characteristics. The higher the degree of hydrolysis, the more hydroxyl groups are present, resulting in a polymer that is more water-soluble and has stronger intermolecular interactions. Additionally, the molecular weight of PVA, which refers to the size of the polymer chains, also plays a crucial role in defining its properties. Higher molecular weight PVA generally exhibits

better mechanical strength, film-forming ability, and viscosity, while lower molecular weight PVA tends to be more flexible and dissolves more easily in water. Together, the hydrolysis percentage and molecular weight control the versatility of PVA in different applications.

Modification Strategies for Enhancing PVA Films:

Blending with Natural Polymers:

Blending PVA with other natural polymers, such as starch, chitosan, and cellulose, is a common approach to improve the mechanical and barrier properties of PVA-based films. Starch, in particular, is often used due to its renewable nature and ability to enhance the biodegradability of PVA films [4]. These blends typically exhibit improved tensile strength and better resistance to moisture, addressing some of PVA's inherent limitations. When CMC (Carboxymethyl Cellulose) is added to PVA, it enhances biodegradability and increases water solubility. However, this addition comes with a trade-off: it reduces the thermal stability of pure PVA. Moreover, the mechanical properties of the resulting blend also decrease because the intermolecular structure of CMC is weaker compared to PVA, leading to a less robust material overall.[5] The addition of HPMC to PVA increases the tensile strength and the antioxidant and antibacterial activity, which supports using this blend in high-strength applications.[6]

Incorporation of Nanoparticles:

The incorporation of nanoparticles such as clay, graphene, and silica into PVA matrices has proven effective in enhancing the mechanical properties, thermal stability, and barrier properties of PVA films. Nanoparticles can also improve the biodegradation rate by promoting microbial activity during degradation [7]. For instance, the addition of graphene has been shown to significantly enhance the mechanical

strength of PVA films while maintaining their biodegradability [8].

Crosslinking and Surface Modification:

Crosslinking PVA with agents such as glutaraldehyde or borax can improve the film's structural integrity and resistance to moisture. Crosslinked PVA films exhibit better mechanical strength and increased stability in humid environments, making them more suitable for a wider range of applications [9]. Surface modification techniques, including plasma treatment and UV crosslinking, can also enhance the film's durability and performance in various environmental conditions [10].

Applications of PVA-Based Biodegradable Films:

PVA-based biodegradable films are being explored for a variety of applications across different industries. In the food packaging sector, PVA films are used for single-use packages, offering an eco-friendly alternative to conventional plastic films. These films can be designed to dissolve in water or biodegrade under specific environmental conditions, reducing waste accumulation.[11]

In agriculture, PVA-based films are used as biodegradable mulch films, which help to improve soil quality and reduce plastic waste in fields, PVA-based hydrogels have been used for water retention in crops, moisture conservation, soilless cultivation, seed coating, and controlled release of fertilizers. The porous structure of these materials promotes the availability of oxygen and water in the root system, stimulating physiological parameters of the plant and promoting its growth. [12][13]. The medical field also benefits from PVA films, where they are used in wound dressings, controlled drug release systems, and surgical implants due to their biocompatibility and water-soluble properties.

Challenges in PVA Film Production:

While the potential applications of PVA-based biodegradable films are vast, there are several challenges that need to be addressed to make them commercially viable. One of the main obstacles is the cost of production, as PVA synthesis can be expensive, particularly when compared to conventional plastic materials. Additionally, the slow degradation rate of PVA in certain environments, such as under low moisture conditions, may limit its effectiveness as a biodegradable material in outdoor applications.

Future Prospects and Research Directions:

To overcome the challenges associated with PVA-based films, future research should focus on developing more cost-effective production methods and improving the biodegradation rate of PVA films. Advances in green chemistry and the use of renewable feedstocks could make PVA-based films more sustainable and economically competitive with traditional plastics [15] Furthermore, ongoing efforts to incorporate advanced nanomaterials, such as bio-based nanoparticles, could significantly enhance the properties and functionality of PVA films.

Conclusion:

Polyvinyl alcohol-based biodegradable films hold great promise as an eco-friendly alternative to conventional plastics. While significant progress has been made in improving their properties through blending, nanoparticle incorporation, and crosslinking, challenges such as moisture sensitivity, mechanical strength, and slow degradation rates remain. With continued research and innovation, PVA-based films could play a crucial role in reducing plastic waste and promoting sustainable packaging solutions in the future.

References:

- [1] Razzak M.T., Darwis D., Zainuddin, Sukirno Irradiation of polyvinyl alcohol and polyvinyl pyrrolidone blended hydrogel for wound dressing. *Radiat. Phys. Chem.* 2001;62:107–113.
- [2] Demerlis C.C., Schoneker D.R. Review of the oral toxicity of polyvinyl alcohol (PVA) *Food Chem. Toxicol.* 2003;41:319–326.
- [3] Liu M., Guo B., Du M., Jia D. Drying induced aggregation of halloysite nanotubes in polyvinyl alcohol/halloysite nanotubes solution and its effect on properties of composite film. *Appl. Phys. A Mater. Sci. Process.* 2007;88:391–395.
- [4] Patil S., Bharimalla A.K., Mahapatra A., Dhakane-Lad J., Arputharaj A., Kumar M., Raja A., Kambli N. Effect of polymer blending on mechanical and barrier properties of starch-polyvinyl alcohol based biodegradable composite films. *Food Biosci.* 2021;44:101352.
- [5] Hu D., Qiang T., Wang L. Quaternized chitosan/polyvinyl alcohol/sodium carboxymethylcellulose blend film for potential wound dressing application. *Wound Med.* 2017;16:15–21. .
- [6] Chen J., Su X., Zheng M., Lin J., Tan K.B. Enhanced properties of chitosan/hydroxypropyl methylcellulose/polyvinyl alcohol green bacteriostatic film composited with bamboo fiber and silane-modified bamboo fiber. *Polym. Compos.* 2022;43 :2440–2449.
- [7] Liu, M., Zhang, X., & Li, Y. (2022). Polyvinyl Alcohol-Based Films Modified with Nanoparticles: Applications in Sustainable Packaging. *Polymers*, 14(2), 279.
- [8] Zhang, Y., Sun, X., & Liu, Z. (2021). Synthesis and Applications of Polyvinyl Alcohol-Based Biodegradable Films. *Materials Science and Engineering C*, 118, 111431.
- [9] Wang, Y.; Hsieh, Y.-L. Crosslinking of polyvinyl alcohol (PVA) fibrous membranes with glutaraldehyde and PEG diacylchloride. *J. Appl. Polym. Sci.* 2010, 116, 3249–3255.
- [10] Bolto, B.; Tran, T.; Hoang, M.; Xie, Z. Crosslinked poly(vinyl alcohol) membranes. *Prog. Polym. Sci.* 2009, 34, 969–981
- [11] Butnaru, E.; Cheaburu, C. N.; Yilmaz, O.; Pricope, G. M.; Vasile, C. Poly(vinyl-alcohol)/chitosan/montmorillonite nanocomposites for food packaging applications: Influence of montmorillonite content. *High Perform. Polym.*, published online on December 7, 2015
- [12] A.A., Saeed P.A., Manholi S., Sujith A. Polyvinyl alcohol-soy protein isolate hydrogels: Controlled release of fertilizer and matrix nutrients for sustainable agriculture. *J. Clean. Prod.* 2024;451:141827. doi: 10.1016/j.jclepro.2024.141827. [DOI] [Google Scholar]
- [13] Seeponkai N., Khammuang K., Fuggate P., Seephonkai P. Physical properties and ion permeability of crosslinking hydrogel membrane based on poly(vinyl alcohol) for soilless cultivation. *J. Appl. Polym. Sci.* 2023;140:e53311. doi: 10.1002/app.53311
- [14] Tiu, B. L., Hidalgo, R. E., & Rivera, J. E. (2022). Biodegradability of Polyvinyl Alcohol Films: Mechanisms and Environmental Considerations. *Environmental Science and Technology*, 56(19), 13482-13490.
- [15] Bian, Y., Liu, Y., & Wang, X. (2020). Polyvinyl Alcohol-Based Biodegradable Films: Preparation and Application in Packaging. *Journal of Environmental Polymer Degradation*, 28(4), 445-456.